



































# Thin Brick Range Technical Data Sheet

Product Range	Product Name	Dimension Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Units per Square Metre	Pack Size	Maximum Cold Water Absorption (%)	Initial Rate of Absorption (IRA) (kg/m <sup>2</sup> min)	Coefficient of Expansion Factor (mm/m)	Durability Class	Liability to Efflorescence	Lime Pitting Liability	LRV
Thin Brick	Limewash Corner Unit			WA	230	110	76	DW0		1008	<17	4.0-8.0		General Purpose	Slight	Slight	
Thin Brick	Original Facing Unit			WA	230	22	76	DW0	48.5	2160	<17	4.0-8.0		General Purpose	Slight	Slight	
Thin Brick	Castellana Corner Unit			WA	230	110	76	DW1		1200	<6	<0.8		Exposure Grade	Slight		67
Thin Brick	Limewash Facing Unit			WA	230	22	76	DW0	48.5	2160	<17	4.0-8.0		General Purpose	Slight	Slight	
Thin Brick	Azul Facing Unit			WA	230	22	76	DW1	48.5	1920	<6	<0.8		Exposure Grade	Slight		13.1
Thin Brick	Glazed White Corner Unit			WA	230	110	76	DW1		1200	<6	<0.8		Exposure Grade	Slight		66.4
Thin Brick	Wild Storm Facing Unit			WA	230	22	76	DW0	48.5	2160	<15	4.0-8.0	<1.0	General Purpose	Slight	Slight	14.1
Thin Brick	Aged Red Corner Unit			WA	230	110	76	DW0		1008	<17	4.0-8.0		General Purpose	Slight	Slight	
Thin Brick	Cloudy Silver Corner Unit			WA	230	110	76	DW0		1008	<15	4.0-8.0	<1.0	General Purpose	Slight	Slight	22.8
Thin Brick	Castellana Facing Unit			WA	230	22	76	DW1	48.5	1920	<6	<0.8		Exposure Grade	Slight		67
Thin Brick	Glazed White Facing Unit			WA	230	22	76	DW1	48.5	1920	<6	<0.8		Exposure Grade	Slight		66.4
Thin Brick	Glazed Black Facing Unit			WA	230	22	76	DW1	48.5	1920	<6	<0.8		Exposure Grade	Slight		1
Thin Brick	Miro Facing Unit			WA	230	22	76	DW1	48.5	1920	<6	<0.8		Exposure Grade	Slight		63.7
Thin Brick	Cloudy Silver Facing Unit			WA	230	22	76	DW0	48.5	2160	<15	4.0-8.0	<1.0	General Purpose	Slight	Slight	22.8
Thin Brick	Miro Corner Unit			WA	230	110	76	DW1		1200	<6	<0.8		Exposure Grade	Slight		63.7
Thin Brick	Grey Cashmere Corner Unit			WA	230	110	76	DW0		1008	<15	4.0-8.0	<1.0	General Purpose	Slight	Slight	45.5
Thin Brick	Azul Corner Unit			WA	230	110	76	DW1		1200	<6	<0.8		Exposure Grade	Slight		13.1

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.

Please note: FRL applies up to 3m high - restrained on top and bottom.

Product Range	Product Name	Dimension Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Units per Square Metre	Pack Size	Maximum Cold Water Absorption (%)	Initial Rate of Absorption (IRA)(kg/m <sup>2</sup> min)	Coefficient of Expansion Factor (mm/m)	Durability Class	Liability to Efflorescence	Lime Pitting Liability	LRV
Thin Brick	Original Corner Unit			WA	230	110	76	DW0		1008	<17	4.0-8.0		General Purpose	Slight	Slight	
Thin Brick	Grey Cashmere Facing Unit			WA	230	22	76	DW0	48.5	2160	<15	4.0-8.0	<1.0	General Purpose	Slight	Slight	45.5
Thin Brick	Wild Storm Corner Unit			WA	230	110	76	DW0		1008	<15	4.0-8.0	<1.0	General Purpose	Slight	Slight	14.1
Thin Brick	Opaque Slate Facing Unit			WA	230	22	76	DW0	48.5	2160	<15	4.0-8.0	<1.0	General Purpose	Slight	Slight	24.9
Thin Brick	Romero Corner Unit			WA	230	110	76	DW1		1200	<6	<0.8		Exposure Grade	Slight		12
Thin Brick	Romero Facing Unit			WA	230	22	76	DW1	48.5	1920	<6	<0.8		Exposure Grade	Slight		12
Thin Brick	Glazed Black Corner Unit			WA	230	110	76	DW1		1200	<6	<0.8		Exposure Grade	Slight		1
Thin Brick	Opaque Slate Corner Unit			WA	230	110	76	DW0		1008	<15	4.0-8.0	<1.0	General Purpose	Slight	Slight	24.9
Thin Brick	Aged Red Facing Unit			WA	230	22	76	DW0	48.5	2160	<17	4.0-8.0		General Purpose	Slight	Slight	

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.

Please note: FRL applies up to 3m high - restrained on top and bottom.